


Bs-Temperature

H=1194A/m




Initial permeability μ_i	25°C	2500±25%
Saturation magnetic flux density B_s (mT)	25°C	570
Curie temperature T_c (°C)		≥220
Electrical resistivity ρ (Ω·m)		3


Curie temperature T_c (°C)	≥220
Electrical resistivity ρ (Ω·m)	3

Test core : Toroid(mm)


- OD : 25
- ID : 15
- H : 7.5



μ_i -Temperature



B-H



μ_i -Frequency

