



### Bs-Temperature




Initial permeability	$\mu_i$	25°C	1500±25%	
Saturation magnetic flux density	$B_s(\text{mT})$	25°C	530	
		100°C	440	
Remanence	$B_r(\text{mT})$	25°C	210	
		100°C	70	
Coercivity	$H_c(\text{A/m})$	25°C	24	
		100°C	13	
Core loss	$P_{cv}(\text{kW/m}^3)$	25°C	1000	
		100kHz 200mT	100°C	480
Curie temperature	$T_c(°\text{C})$		≥285	
Electrical resistivity	$\rho(\Omega\text{-m})$		3	
Density	$d(\text{kg/m}^3)$		$4.8 \times 10^3$	

### $\mu_i$ -Temperature



### B-H



### $\mu_i$ -Frequency

