



Complex permeability vs. Frequency




Initial permeability	μ_i	25°C	650±20%
Saturation magnetic flux density	B_s (mT)	25°C	400
Relative loss factor	$\tan\delta/\mu_i$	25°C	≤15
Relative temperature coefficient	α_{μ}		(×10 ⁻⁶)
Curie temperature	T_c (°C)		>185
Electrical resistivity	ρ		(×10 ⁻⁶)

Relative loss factor vs. Frequency



Structure

Flux density vs. Temperature



Initial permeability vs. Temperature

