



CD : 12.7

ID : 7.9

H : 6.5

Initial permeability	μ_i	25°C	1000±20%
Saturation magnetic flux density	Bs(mT) 4000A/m	25°C	320

